


COMPLEMENTARY PRODUCTS



PHYSICAL PROPERTIES

HR (type 1) Expanded Polystyrene

Thermal Resistance (ASTM C518 C177) Thickness of 25 mm (1")	RSI-0.65 R-3.7
Vapour Permability (ASTM E96) Thickness of 25 mm (1")	5.25 perm 300 ng/Pa·s·m²
Compressive Strength (ASTM D1621) Thickness of 38 mm (1 1/2")	80 kPa 11.64 lbs/in²
Flexural Strength (ASTM C518 C203) Thickness of 38 mm (1 1/2")	170 kPa 24.78 lbs/in²
Water Absorption (ASTM D2842) Thickness of 38 mm (1 1/2")	6%
Density (ASTM D1621)	16.01 kg/m³ 1 lbs/ft³
Limiting Oxygen Index (ULC S-701) % minimum	24%
Dimension Stability (ASTM D2126) % max. of linear change	1.5%

DESCRIPTION

Expanded polystyrene insulation board, shiplapped on four sides, factory laminated to a 13 mm (1/2") cover board, square end cut, designed to insulate flat or low slope roofs.

CERTIFICATIONS



- Meets CAN/ULC S-107 Standard
- C7 and C12 under CAN/ULC S-126M Standard
- UL Standard 790 (ASTM E 108)
- UL Class A with most roofing membrane systems (See UL Directory of Roofing Systems and Materials)

INSTALLATION

1. If adhered with adhesive, refer to the technical data sheet of the adhesive used for application recommendations.
2. Place the panels in close contact, in parallel rows and without deformation or empty space, as indicated in the shop drawing.
3. Fill joints more than 5 mm (3/16").
4. If mechanically attached, use the appropriate LEXCOR LEXGRIP screws and plates. Follow FM recommendations for the number of mechanical fasteners to be used per panel.

ADVANTAGES

Fast Installation

One step is saved on site since the insulation panel is already laminated to the cover board.

Low Water Absorption

The closed cell walls are waterproof and as such, water can only penetrate in channels located between polystyrene cells that are held together.

High-Dimensional Stability

According to industry standards, EPS is one of the leaders in terms of size maintenance. This helps the system to remain fully waterproof at all times.

[Continued on back](#)

IZOLON® R+

TYPE HR

FLAT EXPANDED POLYSTYRENE INSULATION BOARD

PHYSICAL PROPERTIES

Cover Board

Min. requirement as per ASTM C1289 or CAN/ULC S704

Nominal Thickness	12.5 mm 0.5"
Thermal Resistance (ASTM C518)	RSI-0.44 R-2.5
Water Vapour Transmission (ASTM E96)	< 1.5 perm < 85.8 ng/Pa·s·m ²
Water Absorption (ASTM C209) (ASTM C1763) (ASTM D2842)	< 4.0% < 4.0% < 3.5%
Compressive Strength (ASTM D1621)	90¹
Dimensional Stability (ASTM D2126)	< 0.5%
Tensile Strength (ASTM D1623)	> 95 kPa > 2000 psf
Smoke Development (ASTM E84/UL723)	< 450²
Flame Spread (ASTM E84/UL723)	< 75²
Service Temperature	-73°C to 121°C (-100°F to 250°F)

¹551 kPa (80 psi) minimum, up to 758 kPa (110 psi)

²Numerical ratings are not intended to reflect performance under actual fire conditions. Flame spread index of ≤75 and smoke development ≤450 meet code requirements for foam plastic roof insulation. Physical properties listed above are presented as typical average values as determined by referenced ASTM test methods and are subject to normal manufacturing variation.

SIZES

Width x Length*	1219 mm x 1219 mm 48" x 48"
Thickness - Straight Edge	25 mm to 610 mm 1" to 24"
Thickness - Shiplapped Edge	51 mm to 305 mm 2" to 12"
Shiplap	13 mm to 16 mm 1/2" to 5/8"
Number of Panels per Skid	Varies according to thickness

*Order sizes available on special order

Captive Gas; 98% Air and 2% Plastic

This formula has been used for more than 50 years. It does not contain any VOC, CFC's, HCFC's, Formaldehyde or any gas that can impact the ozone layer. Furthermore, this provides the product with premium features including its light weight and the maintenance of R-value.

Meets High Standards

Helps to reach Novoclimat (in Quebec if applicable), EnergyStar (Ontario and the Maritimes) and R-2000 (Canada) insulation levels.



PRODUCT WARRANTY

Thermal Value is 100% Guaranteed

The thermal resistance of the product is 100% guaranteed free of charge for a period of at least 40 years.

